

Old English (18 colours)

Old English is an aniline finished leather, tanned to ensure a pleasing distressed or aged finish from new. Extra fat liquors are applied during tanning, to give the leather a slightly waxy feel. These leathers are designed to allow the natural marking variations of the leather to show through to the finish coat. Pull-up leathers do not have a consistent colour density across the whole hide. They are designed to change colour and sheen when pulled or stretched. They are not as colour fast as pigmented hides and are designed to allow furniture to age and relax through use and over time. Furniture should be protected from direct sunlight and not placed next to radiators. Evidence of marks and scarring will be seen through the surface finish. Each hide will be unique, and so will the furniture on which it is used. Therefore swatch samples should be regarded as no more than a guide, for these types of leather.

SPECIFICATIONS

| | |
|---------------------------------------|---|
| Category: | Aniline |
| Raw Material: | European |
| Country of Origin: | Italy |
| Average Hide Size: | 55 sq ft |
| Average Thickness: | 0.9-1.1 mm |
| Test Method: | ISO 2589 |
| Test Method: | ISO 5402 |
| Colour Fastness To Light: | Min 3 Blue Scale |
| Test Method: | EN ISO 105-B02 |
| Colour Fastness To Rubbing: | Dry 50 Cycles - Min 3 Grey Scale Wet 20 Cycles - Min 3 Grey Scale Perspiration 20 Cycles - Min 3 Grey Scale |
| Test Method: | EN ISO 11640, EN ISO 11641 |
| Finish Adhesion: | Min 2 N/10mm |
| Test Method: | ISO 1164 |
| Tear Strength: | Min 20 N |
| Test Method: | EN ISO 3377-1 |
| California Technical: | Class 1 |
| Test Method: | Cal Tech Bulletin 117 |
| Cigarette Ignition Resistance: | Class 1 |
| Test Method: | UFAC/NFPA 260 |

COLOURS

Alga
 Black
 Bruciato
 Buckskin
 Burgundy
 Chestnut
 Dark Brown
 Gamay
 Hazel
 Olive
 Parchment
 Red Brown
 Saddle
 Sand
 Smoke
 Tan
 Terracota
 Wine